

PRODUCT	FABRICS	TIME	TEMP	PRESSURE	PEEL	LAYER	COVER & SEAL
AURORA-B	100% Cotton 100% Polyester 50/50 Blends	15 sec	315° F	Medium	Cold	Yes	No
ENVICTA CUT	100% Cotton 100% Polyester 50/50 Blends	8-10 sec	305° F	Medium	Warm/Cold	Possible	Only to Layer
FLEX-ALL	All-Fabric Film Nylon Coated Nylon Uncoated	8-12 sec	310° F	Medium	Hot or Cold	Yes	Only to Layer
GLITTER CUT	100% Cotton 100% Polyester 50/50 Blends	8-10 sec	305° F	Medium	Hot/Warm	No	No
HTV BLOCK	All-Fabric Film Nylon Coated Nylon Uncoated	8-10 sec	285° F	Medium	Hot or Cold	Yes	Only to Layer
METAL	100% Cotton 100% Polyester 50/50 Blends	8-10 sec	305° F	Medium	Cold	No	Only for Matte
NEXXUS	100% Cotton 100% Polyester 50/50 Blends	8-10 sec	305° F	Medium	Cold	Yes	No
R-PUFF	100% Cotton 100% Polyester 50/50 Blends	8-10 sec	300° F	Medium	Hot/Warm	No	No
REFLECT	100% Cotton 100% Polyester 50/50 Blends	10 sec	320° F	Medium	Cold	Yes	No
SUNSATIION	100% Cotton 100% Polyester 50/50 Blends	10-12 sec	300° F	Medium	Warm	Yes	No
ULTRA-CLEAR	All-Fabric Film Nylon Coated Nylon Uncoated	10-12 sec	310° F	Medium	Warm	Yes	Only to Layer
WIZ-KUT	100% Cotton 100% Polyester 50/50 Blends	8-12 sec	300° F	Medium	Hot or Cold	Yes	Only to Layer